


6'2" v2 GfK/CfK Deck (XPS 30 & 2mm Rollenkork) 356g Fasern


Sandwich Deck = 115g Fasern

100g/m² - HTC 300g/m² - HTC



Face Sheet Deck = 241g Fasern


208g/m² - E-Glas 392g/m² - E-Glas 472g/m² - E-Glas
288g/m² - E-Glas 416g/m² - E-Glas 496g/m² - E-Glas
368g/m² - E-Glas 576g/m² - E-Glas



6'2" v2 GfK/CfK Rumpf (XPS 30 & 2mm Rollenkork) 288g Fasern

Sandwich Rumpf = 101g Fasern

150g/m² - HTC



Face Sheet Rumpf = 187g Fasern

208g/m² - E-Glas 312g/m² - E-Glas

