

Kalkulation Materialmix Directional

Materialmix	Ingo 6.2 XPS & Kork	Altern. XPS & Kork	XPS & C70.75	EPS & Kork	EPS & C70.75
Volume	26.9 Liter				
Gew. Faser : Gew. Epoxy	1.0	1.2	1.2	1.2	1.2
Kern	807 g	807 g	807 g	404 g	404 g
Abspachteln Sandw. & Blank & Fehler	300 g	250 g	200 g	250 g	200 g
Verklebung Sandwich	1,253 g	1,028 g	788 g	1,028 g	788 g
Plug-Ins & Finnenboxen	5 Fin 390 g	Thruster 290 g	Thruster 290 g	Thruster 290 g	Thruster 290 g
Gewicht vor Laminat	2,750 g	2,375 g	2,085 g	1,972 g	1,682 g
Abspachteln Bubbles & Fehler	100 g	100 g	100 g	100 g	100 g
Laminat Face Sheet	988 g	1,148 g	1,148 g	1,148 g	1,148 g
Gewicht vor Oberfläche	3,838 g	3,624 g	3,334 g	3,220 g	2,930 g
Oberflächenbeschichtung	200 g	200 g	200 g	200 g	200 g
SUMME	4,038 g	3,824 g	3,534 g	3,420 g	3,130 g
Delta	0 g	-214 g	-504 g	-618 g	-908 g